Kayacelon React Yellow CN-4G

NIPPON KAYAKU

- ≪Characteristics ≫
- OKayacelon React Yellow CN-4G is neutral pH fixation reactive dyestuff.
- OIt is a reactive dye that does not require the addition of alkali and fixation occurs by increasing the temperature.
- OWhen used in combination with disperse dye that can be neutrally dyed, one bath dyeing of Polyester and cellulose blended fibers become possible.

☆Color Fastness (Cotton 100%; 130°C Dyeing, pH 7) *Evaluated using JIS L 0804 Grey Scale

Dyeing depth	Light		Perspiration/Light	Washing (ISO Test 2:50°C)		Chlorinated
	ISO	AATCC	1 erspiration/ Light	Change in	Staining on	Water
deptii	4 Grade	20 AFU	ISO (Alkali)	shade	Nylon	10ppm
0.5%	5*	4-5*	3-4	4-5	4-5	2

Light: ISO 105-B02(Xenon-arc Black panel: 53°C) & AATCC 16-3(Xenon-arc Black panel: 63°C)


Perspiration/Light: ISO (Xenon-arc) Chlorinated Water: JIS L 0884 10ppm

☆Dyeing pattern (Cotton 100%; 100°C Dyeing, pH 7)

[Color Sample]














[Strength ratio and the value of L*a*b*]



%o.w.f.	L*	a*	b*
0.03	91.63	-1.90	11.02
0.1	90.81	-2.85	20.90
0.5	89.04	-3.40	37.28
1.0	87.40	-1.90	50.55
2.0	84.96	-0.24	63.10
3.0	84.12	2.36	70.69

NIPPON KAYAKU (THAILAND) CO., LTD.

ADD: 13th Floor, Ramaland Building, 952 Rama IV road, Suriyawongse, Bangrak, Bangkok 10500

TEL: +66-2-235-2843 HP: http://www.kayakuth.co.th





^{*}There is no intentional addition of the components corresponding to restricted substances listed by OEKO-TEX STANDARD 100, Edition 2/2019.